

FRONTIER OFFICE SCREENS FIRE CERTIFICATE



01733 511030
sales@xldisplays.co.uk



TEST REPORT

Client: Macflex International Ltd
 Macflex House
 Hill Farm
 Upper Hayford
 Northants
 NN73NB

Entry No: 84141-01

Date received: 04/05/2017

Client's Description: Sample of fabric: Mac182, woven screen fabric, colour Purple Drift

Test Required: Flammability BS 5867-2: Type B

Pre-treatment: None

Conditioning: A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C

Date Tests Completed: 11/05/2017

Method of Test: BS EN ISO 15025: 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Flame application time 15 seconds using propane gas

Face of Fabric tested	Fabric length direction			Fabric width direction		
	1	2	3	4	5	6
Specimen number						
Flame reached an edge (☒ or X)	X	X	X	X	X	X
Hole reached an edge (☒ or X)	X	X	X	X	X	X
Flaming debris (☒ or X)	X	X	X	X	X	X

Comments

On the basis of the tests carried out this sample of fabric meets the Type B requirements of BS 5867-2: 2008.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Dale Brockbank
 Materials Testing Manager
 Date of original 11 May 2017
 Date of amendment 12 May 2017

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

