

FRONTIER WATERPROOF CERTIFICATE



01733 511030
sales@xldisplays.co.uk

Our Ref: SW/LS/GL/BR

10 December 2018

Report 331335/6

Page 1 of 2

Camira Fabrics Limited
Meltham Mills
Meltham
Huddersfield
West Yorkshire
HD9 4AY

Contact: Katy Longstaff

DATE RECEIVED	: 23 OCT 2018
QUALITY/REFERENCE	: VITA (C)
REPUTED FIBRE CONTENT	: NOT GIVEN
FABRIC DESCRIPTION	: LEATHER
COLOUR/DESIGN	: AMERICANO
STYLE NUMBER	: CALL 8348
ORDER NUMBER	: 934
PERFORMANCE STANDARD	: NOT SPECIFIED



REQUEST: Hydrostatic head



S. WISEMAN
LABORATORY DIRECTOR



L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

10 December 2018

Report 331335/6

Page 2 of 2

PHYSICAL

Hydrostatic Head BS 3424-26:1990 Method 29A

Sample area	100cm ²
Test atmosphere	20°C 65% R.H
Water temperature	20°C
Rate of rise of water pressure	60cm/1min

As Received	Test 1	>400 cms/H ₂ O
	Test 2	>400 cms/H ₂ O
	Test 3	>400 cms/H ₂ O
	Test 4	>400 cms/H ₂ O
	Test 5	>400 cms/H ₂ O
	Mean	>400 cms/H ₂ O

